

TECHNICAL DATA SHEET

GAP 70 – Plastfill – polyester putty for plastic – 1kg + hardener

PRODUCT DESCRIPTION

GAP 70 is a universal 2-component polyester putty designed to be used on plastic surfaces. Its unique formulation combines good adhesive properties, easy mixing and application and easiness in sanding.

Colour shade Anthracite

Mixing ratio 100 : 1-3

Hardener GAP 51 hardener

Pot life 3 – 5 min.

Curing time Object temp. 20°C: sandable after 20 – 30 min.
Object temp. 60°C: sandable after approx. 4 – 5 min.

VOC regulation

EU limiting value for the product (cat. B/b): 250 g/l
This product contains max. 5g/l VOC (0.04 lbs/gal)

APPLICATION

Apply at minimum +10°C and at max. 80% relative air humidity

SPECIAL REMARKS

The substrate must be clean, dry and free of grease. Slightly sanded surfaces! Remove old layers of paint or primer, which are not adhesive or fully dry. Mix well GAP 70 and GAP 51 hardener. Verify adhesion on TPO recycled materials before continuing with the repair.

	VbF:	hazardous materials ordinance:
GAP 70	n/a	flammable, Xn contains styrene
Hardener	n/a	Xi irritating, oxidizing, contains benzoyl peroxide

Storage

18 months

The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the tapes suitability for their own applications.